

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup>:</b> <b>C04B 22/06 // 24/22</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/12149</b> <b>(43) International Publication Date:</b> 26 March 1998 (26.03.98)
<b>(21) International Application Number:</b> PCT/SE97/01350 <b>(22) International Filing Date:</b> 14 August 1997 (14.08.97) <b>(30) Priority Data:</b> 9603418-6 19 September 1996 (19.09.96) SE <b>(71) Applicant (for all designated States except US):</b> EKA CHEMICALS AB [SE/SE]; S-445 80 Bohus (SE). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> BERGQVIST, Hans [SE/SE]; Skogens Gård 95, S-423 50 Torslanda (SE). CHANDRA, Satish [SE/SE]; Karl Gustavsgatan 22B, S-411 25 Göteborg (SE). <b>(74) Agent:</b> SCHÖLD, Zaid; Eka Chemicals AB, Patent Dept., P.O. Box 11556, S-100 61 Stockholm (SE).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW). Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> A METHOD FOR PREPARATION OF A HARDENING COMPOSITION  <b>(57) Abstract</b>  A method for preparing concrete or mortar in which a mixture of a hydraulic binder, aggregates, water, and colloidal silica is prepared. The relative standard deviation of the particle size distribution by numbers of the colloidal silica is at least about 30 %. The invention also relates to concrete or mortar obtainable by the method.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NI	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

A method for preparation of a hardening composition

The present invention relates to a method for preparation of concrete or mortar having improved strength and durability properties. It also relates to concrete and mortar obtainable by the method, and to the use of said concrete, particularly as construction concrete, as well as to the use of said mortar.

Concrete is an artificial stone, commonly used as a building material, in which aggregates of suitable sizes are bound together by a matrix of a hydraulic binder. Usually the aggregates are stones, in the broad sense, and the hydraulic binder a cement. Concrete normally contains more aggregates than hydraulic binder, at least when calculated on volume basis. The aggregates commonly have a particle size distribution in the range of about 0.01 - 100 mm. In order to prepare concrete the aggregates and the hydraulic binder are mixed with water. Furthermore, concrete may contain certain additives such as setting and hardening additives, usually called accelerators, or workability additives, usually called superplasticiser. Mortar is distinguished by the maximum size of its aggregates: in general, mortar contains only aggregates with a maximum size of about 2-4 mm, e.g. sand. The concepts of cement, concrete, and mortar are furthermore extensively discussed in Ullman's encyclopedia of industrial chemistry, 5th ed., Vol. A5, pp. 490-538, VCH, Weinheim, Germany 1986, hereby incorporated by reference. Below, mortar is comprised, for brevity's sake, by the concept of "concrete".

One important property of concrete is obviously its strength. An important parameter controlling concrete strength is the water:cement ratio. Other factors are the type of cement, curing conditions, moisture content, degree of hydration of the cement, and the grading and shape of aggregates. If sufficient water is provided, the hydration of cement will continue over a period of several years, and concrete strength may increase continuously during this time. Conventionally, high strength is achieved by using a low water:cement ratio; superplasticisers are often used in this connection as they permit the use of lower water:cement ratios. Another way of improving the strength is to add silica fume, which is a pozzolanic waste material from silicon and ferrosilicon industries, having particle sizes of about 0.1-0.2 mm. Silica fume contains however unburnt coal, that gives the concrete a dark, usually undesired, colour, as well as other impurities, such as small quantities of metallic silicon that may cause explosion spalling of the concrete if it gets into contact with water.

Wagner and Hauck disclose in Hochsch. Archit. Bauwes. - Weimar 40 (1994) 5/6/7, pp. 183-7 the use of synthetically produced, chemically pure, and completely amorphous silica having an average particle size of 15 nm, which they call "nanosilica", instead of silica fume, which is referred to as "microsilica". The nanosilica particles are indicated to have specific surface areas in the range of 180 - 230 m<sup>2</sup>/g, suggesting a rather narrow

particle size distribution; in this connection it should be said that according to "The Chemistry of Silica", Ralph K. Iler, Wiley & Sons 1979, pp. 346-7, hereby incorporated by reference, the specific surface area of silica may be transformed into the corresponding particle size, and vice versa, using the formula  $2720/A_d = d_s$ , where  $A_d$  is the specific surface area in  $m^2/g$  and  $d_s$  is the particle size in micrometers. The impurity problems associated with silica fume are greatly overcome by the use of nanosilica. The concrete strength development is indicated to be about the same as if microsilica were used; the early strength development, i.e. from 1 to 7 days, is inferred by table 2 of the reference to be at most 36%. Agglomeration of the nanosilica is not discussed.

10 In EP-A2-0,519,155 a silica sol similar to nanosilica is used in shotcrete, primarily to provide the shotcrete with better cohesive properties, which in turn gives a lower degree of dust formation and rebound during the shotcreting. The cohesive effect is accomplished by promoting aggregation of the colloidal silica. The disclosed silica sol, which have particle sizes in the range of 7-40 nm and specific surfaces in the range of 50-700  $m^2/g$ , shows a  
15 positive impact on the early strength compared to the effect of silica fume. The development of compressive strength from one to seven days is, in absence of accelerators, about 58%. Strength at later age is not mentioned. It has however been found (by the inventors of the present invention) that aggregation, i.e. gelling, coagulation, flocculation, or coarsening, of the colloidal silica has a negative influence on the long term strength when  
20 compared to concrete in which silica fume is used, especially when higher doses of silica colloid are used, or if not mixed properly with the concrete mixture; this is probably due to encapsulation of the cement particles by the silica, which in turn is a hindrance to further hydration of the cement particles. No suggestion is given in EP-A2-0,519,155 about the particle size distribution.

25 The problem to be solved by the present invention is to provide a method for preparing concrete having enhanced early strength while having a good long term strength.

This problem is solved by the method defined by appended claim 1. According to this method, a mixture of an hydraulic binder, aggregates, water, and colloidal silica, is prepared, whereby the relative standard deviation of the particle size distribution of the  
30 colloidal silica is at least about 30%, preferably at least about 35%, and in particular at least about 40%. In this context "colloidal silica" means stable dispersions or sols of discrete particles of amorphous silica; this definition is the same as put forward in "The Chemistry of Silica" by Ralph K. Iler, page 312, Wiley & Sons 1979. The relative standard deviation of the particle size distribution is the ratio between the mean particle size by  
35 numbers and the standard deviation of the particle size distribution. "Variation coefficient" and "coefficient of variation" are terms synonymous to "relative standard deviation". The reason behind the positive effect of the broad particle size distribution on the strength para-

meters is not known, although a plausible hypothesis is that the smaller particles have a stabilising influence on the larger ones against aggregation.

The present invention has the additional advantages of providing concrete having good durability, especially against chemical attacks from, for instance, chlorides, sulphates, carbon dioxide, nitrogen oxides, and water. Furthermore, the obtained concrete has a high ultimate strength and good frost resistance. A particular advantage associated with the present invention is that the final concrete products have a most homogeneous and uniform strength.

10 The hydraulic binder is preferably a portland cement.

Preferably, the silica particles used in the present method have an average specific surface area below about  $200 \text{ m}^2/\text{g}$ , in particular below about  $180 \text{ m}^2/\text{g}$ , and preferably in the range of about  $50\text{-}170 \text{ m}^2/\text{g}$ . Above  $200 \text{ m}^2/\text{g}$  it becomes increasingly difficult to counteract aggregation.

It is also preferred that the silica particles used in the present method have a particle size distribution the standard deviation of which is at least about 20 nm. The particle size distribution may be monomodal, i.e. have one particle size with a higher frequency of occurrence than the immediately adjacent sizes, or be polymodal, i.e. have two or more such particle sizes.

The silica particles preferably have a mean particle size by numbers of about 7-50 nm, particularly of about 10-30.

In the present method the particles are preferably added in form of an aqueous suspension containing about 8-60 percent by weight, in particular about 30-50 percent by weight, of silica. The particles are generally of a size of about 5-200 nm, preferably 10-100 nm, and they are preferably added to the mixture in an amount of about 1-8 percent by weight, in particular about 1-5 percent by weight, and especially about 2 percent by weight, calculated on the weight of the hydraulic binder. According to a preferred embodiment of the present invention the method also includes addition of a superplasticiser. Any suitable superplasticiser may be used, but it is preferred that it comprises a sulphonated naphthalene-formaldehyde resin, a sulphonated melamine-formaldehyde resin, or a sulphonated melamine-urea-formaldehyde resin, or a mixture thereof. Exemplary of useful superplasticiser are those disclosed in WO 91/12214 and EP 692,465, both of which are hereby incorporated by reference.

35 A part or all of the superplasticiser is preferably added to the concrete mixture before the colloidal silica, as this way of adding has shown to have a stabilising effect on the colloidal silica. In a particularly preferred embodiment of the present method about 35-

55 percent by weight, preferably about 55 percent by weight, of the superplasticiser, based on the total amount of superplasticiser, is added before the colloidal silica.

The colloidal silica need not be stabilized by any stabilizing agent. It could, for instance, be silica sol prepared by the ion-exchange method as set forth in "The Colloid Chemistry of Silica", Horacio E. Bergna (Ed.), American Chemical Society 1994. Preferably, however, the colloidal silica is stabilized, in particular with alkaline substances, advantageously by ions of alkaline metals, e.g. of Na, K, or Li, or by ammonium ions ( $\text{NH}_4$ ), or a combination thereof. In a preferred embodiment the amount of stabilizing alkaline substance is governed by a molar ratio  $\text{SiO}_2:\text{M}_2\text{O}$  of from about 150:1 to about 300:1, whereby M represents Na, K, Li, or  $\text{NH}_4$ .

Accelerators, such as conventionally used in shotcrete, are preferably not used, or only used in insignificant amounts, when preparing concrete according to the present method.

According to a preferred embodiment of the present invention, concrete is prepared by mixing about 100 parts by weight of hydraulic binder; about 100-1000 parts by weight of aggregates; up to about 5 parts by weight of colloid silica; up to about 5 parts by weight of superplasticiser; and about 25-75 parts by weight of water.

The present invention also relates to concrete obtainable by the method according to the present invention as set forth above. According to one embodiment of the present invention concrete obtainable by said method is preferably used as construction concrete, which concept in the present context does not comprise shotcrete. The concept of "concrete" also comprises special concretes such as heavyweight concrete, lightweight concrete, fibre-reinforced concrete, and massive concrete.

Below, the present invention is illustrated by means of non-limiting examples.

Example 1: An anionic silica sol stabilized with  $\text{NH}_4^+$  and containing less than 0.05% of  $\text{Na}_2\text{O}$  was used. The specific surface area was  $80 \text{ m}^2/\text{g}$ , the mean particle diameter by numbers was 35 nm with a standard deviation by numbers of 25 nm, i.e. the relative standard deviation was 71%. 95% by numbers of the particles had a size within the range from 5-150 nm. The silica sol was present as a dispersion containing 40 percent by weight of the solid particles, based on the dispersion. A mixture was prepared of 500g standard portland cement, 1500g standard sand 1,2,3, 7.5g superplasticiser "Mighty 100", which is a sulphonated naphthalene formaldehyde condensate available from the Japanese company Kao Chemicals, and 62.5g of the silica sol dispersion, whereby 50% of the total added amount of superplasticiser was added to the mixture before addition of the silica sol. The water:cement ratio was 0.4. Fresh density was  $2195 \text{ kg/m}^3$ , and  $4 \times 4 \times 16 \text{ cm}$  mortar prism samples were cast. The samples were cured for one day in steel frames, five days in water, and later in a climate room at  $20^\circ\text{C}$  and 55% RH. The flexural and com-

pressive strengths were measured after one, three, and seven days, by means of standard methods SS 13 42 33 and SS - EN 196.1, respectively. The results are set forth in Table I below.

Table I		
Days	Flexural strength, MPa	Compressive strength, MPa
1	5.4	30.7
3	8.8	40.2
7	6.5	50.7
strength development in 1-7 days, %	20	65

5 As can be seen in Table I the development of compressive strength from one to seven days clearly surpasses the development suggested in EP-A2-519,155; in fact even the actual compressive strength is higher.

Example 2 Mortars were made with different amounts of an anionic colloidal silica sol containing 0.22% of  $\text{Na}_2\text{O}$ . The specific surface area of the silica particles was  $80 \text{ m}^2/\text{g}$ ,  
 10 the mean particle diameter by numbers was 62 nm with a standard deviation by numbers of 28 nm, i.e. the relative standard deviation was 45%. 95% by numbers of the particles had a size within the range of  $62 \text{ nm} \pm 56 \text{ nm}$ . The silica sol was present as a dispersion containing 50 percent by weight of the solid particles. The mortars has cement:sand ratios of 1:3. Standard portland cement, supplied by Cements AB, Slite, Sweden, and standard  
 15 sand, grade 1, 2, and 3 were used. Mighty 100 was used as superplasticiser in an amount of 1.5 percent by weight, based on the weight of the cement; about 50% of the plasticiser was added before the colloidal silica sol was added. Table II below shows the weight percentages of silica sol, based on the cement, together with the water:cement ratios, the fresh densities, the air contents, and the consistencies, of the various mortars

Table II					
No.	silica sol, %	w/c ratio	fresh density, kg/m <sup>3</sup>	air, %	consistency, mm
KF3	3	0.41	2300	3.02	135
KF5	5	0.43	2220	5.9	130
KF8	8	0.46	2260	4.70	130

Prisms having the dimensions 4x4x16 cm were cast of the mortars according to Table II. They were demoulded after 1 day, cured in water for 5 days, and in a climate room at 55% RH and 22°C for 22 days. Flexural and compressive strengths were measured after 1, 7, and 28 days, by means of standard method SS 1342 33 and SS-EN 196-1, respectively. The results, given in MPa, are set forth in Table III below.

Table III			
	KF3	KF5	KF8
Compressive strength, 1 day	31.4	33.2	22.3
7 days	51.7	53.0	51.5
28 days	63.7	61.7	64.8
Flexural strength, 1 day	5.88	6.18	4.31
7 days	9.32	9.41	7.26
28 days	12.7	12.1	10.3

Regarding early strength, i.e. in 1-7 days, the best results were evidently obtained with mortar KF5.

KF5 was subjected to some durability test. Chloride-ion penetration was measured by means of a method described in an article by Tang et al. entitled "Rapid determination of chloride diffusivity in concrete applying an electric field", Material Journal, Vol. 89, No. 1, page 49, The American Concrete Institute 1992, hereby incorporated by reference.



and the diffusion coefficient regarding chloride-ion penetration for KF3 was determined to  $3.13 \times 10^{-12} \text{ m}^2/\text{s}$ , whereas a reference sample with no silica sol added showed a diffusion coefficient of  $11.1 \times 10^{-12} \text{ m}^2/\text{s}$ . The carbonation depth was measured by spraying phenolphthalein on a fresh broken surface, substantially perpendicular to the surface of the sample, and measuring the length of penetration indicated by the phenolphthalein. The KF3 sample showed a penetration depth of 1.49 mm after 225 hours, while a reference sample with no silica sol added showed a penetration depth of 12.2 mm after an equally long period of time. Freeze-thaw salt resistance was determined by freezing a KF3 mortar prism in a saturated NaCl solution at  $-20^\circ\text{C}$  for 16 hours and then thawing it in water at ambient temperature for 8 hours. This freeze-thaw sequence was repeated a number of times, whereby each sequence was denominated "a cycle". The freeze-thaw salt resistance was estimated on basis of the weight change of the prisms after certain numbers of cycles. A reference prism with no silica sol added showed a weight loss of 20% after 11 cycles, and after 16 cycles it was broken. The KF3 prism, however, instead showed a weight gain (due to absorption of the salt solution) of about 0.3% at 16 cycles, and even at 35 cycles there was not any noticeable weight loss.

### Claims

1. A method for preparing concrete or mortar, characterised in that it comprises preparing a mixture of a hydraulic binder, aggregates, water, and colloidal silica, wherein the relative standard deviation of the particle size distribution by numbers of the  
5 colloidal silica is at least about 30%.
2. A method according to any preceding claim, characterised in that the silica particles have an average specific surface area below about 200 m<sup>2</sup>/g.
3. A method according to claim 2, characterised in that the particles have an average specific surface area of from about 50 to about 170 m<sup>2</sup>/g.
- 10 4. A method according to any preceding claim, characterised in that the silica particles have a particle size distribution with a standard deviation of at least about 20 nm.
5. A method according to any preceding claim, characterised in that the silica particles have a mean particle size by numbers of from about 7 to about 50 nm.
- 15 6. A method according to any preceding claim, characterised in that the particles are added with an aqueous suspension containing from about 15 to about 50 percent by weight of silica.
7. A method according to any preceding claim, characterised in that the particles are added in an amount of from about 1 to about 8 percent by weight, calculated  
20 on the hydraulic binder.
8. A method according to any preceding claim, characterised in that the preparation of the mixture includes addition of a superplasticiser.
9. A method according to claim 8, characterised in that part of the superplasticiser is added to the mixture before the silica particles.
- 25 10. A method according to claim 9, characterised in that said part of plasticiser is from about 35 to about 55 weight-% based on the total amount of superplasticiser added.
11. A method according to any preceding claim, characterised in that the superplasticiser comprises a sulphonated naphthalene-formaldehyde resin, a sulphonated  
30 melamine-formaldehyde resin, or a sulphonated melamine-urea-formaldehyde resin.
12. A method according to any preceding claim, characterised in that the silica particles are stabilized against aggregation by means of alkali metal ions or ammonium ions.
13. A method according to any preceding claim, characterised in that no  
35 or only an insignificant amount of accelerator is added to the mixture.
14. A method according to any preceding claim, characterised in that the concrete or mortar is prepared by mixing about 100 parts by weight of hydraulic binder;

from about 100 to about 1000 parts by weight of aggregates; up to about 5 parts by weight of colloid silica; up to about 5 parts by weight of superplasticiser; and from about 25 to about 75 parts by weight of water.

15. Concrete or mortar obtainable by the method according to any preceding  
5 claim.

16. Concrete or mortar according to claim 15, with the proviso that it is not shotcrete.

17. Concrete or mortar according to claim 15 or 16, characterised in that it is construction concrete.

10 18. Concrete or mortar according to anyone of claims 15-17, characterised in that it is mortar.

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 97/01350

## A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C04B 22/06 // C04B 24/22

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO:WPI

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 1495811 A (AB ALFONG BETONGHARDNINGSMEDEL & CO., KOMMANDITBOLAG), 21 December 1997 (21.12.97), page 1, line 20 - line 34  -- -----	1-18

☐ Further documents are listed in the continuation of Box C.
 ☒ See patent family annex.

- \* Special categories of cited documents:
- \* "A" document defining the general state of the art which is not considered to be of particular relevance
- \* "E" earlier document but published on or after the international filing date
- \* "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \* "O" document referring to an oral disclosure, use, exhibition or other means
- \* "P" document published prior to the international filing date but later than the priority date claimed
- \* "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \* "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \* "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- \* "&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
5 November 1997	19 -11- 1997
Name and mailing address of the ISA/ Swedish Patent Office Box 5055, S-102 42 STOCKHOLM Facsimile No. +46 8 666 02 86	Authorized officer  May Hallne Telephone No. +46 8 782 25 00

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

01/10/97

International application No.

PCT/SE 97/01350

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 1495811 A	21/12/97	AU 7906575 A	16/09/76
		BR 7501491 A	16/12/75
		CH 603507 A	15/08/78
		DE 2510224 A	25/09/75
		FR 2263987 A,B	10/10/75
		JP 50133223 A	22/10/75
		NL 7503106 A	16/09/75
		SE 7403454 A	15/09/75
<hr/>			